



FINISH

# RUSTIC FINISH

FIN.RUS



Natural Calk rustic finish has the aesthetic effect of a troweled or spot-coated civil plaster, consisting of cured lime putty according to UNI EN 459-1 and selected aggregates and mineral dyes, without cements and chemical additives.

## PRODUCT DESCRIPTION

The Natural Calk rustic finish is ideal for giving facades a rustic effect, and is perfectly suited for even modern works. To ensure bonding to the substrate, a pre-consolidation with Natural Calk Fixative F.S.P.1 substance is recommended; the Natural Calk smoothing mortar can be applied on:  
Raw walls completely finished; Civil plaster;  
To regularize old walls;  
Filling and grouting, finishes on ancient exposed brick walls;  
It is applied to cork, calcium silicate, cellular concrete, wood cement, aspen-aerogel, plasterboard and magnesium calcium.  
TYPE F: fine aggregates. TYPE G: large aggregates

## FEATURES

The Natural Calk rustic finish differs because:  
It is ready to use;  
It adheres perfectly; It resists alkaline aggression;  
It resists bacterial aggression from molds and mosses; It offers effective abrasion resistance;  
It is not flammable;  
Wet specific weight 1,6 kg/l; Vapor permeability  $\mu$ 4; PH 12.

## RULES OF USE AND RECOMMENDATIONS

The Natural Calk rustic finish is applied with a steel trowel; when it starts to adhere, it must be finished with a sponge trowel;  
For other applications, just finish with a steel trowel; Protect the application from rain for about 48 hours;  
Do not apply at air temperatures below 5°C or above 25°C and on masonry overheated by the sun; in hot and windy periods, it is necessary to moisten the walls;  
Before use, shake mechanically until the mixture is homogeneous.

## YIELD

The yield of the Natural Calk rustic finish is on average 2 kg/sqm one coat, on civil plaster. The average coatings per coat consumption is 1.2 kg/sqm by coat.  
In the walls for historical recovery, it varies according to the type of wall. Supplied in 25 kg drums

## ITEM SPECIFICATIONSS

Natural Calk rustic finish for old and patched plasters, stone facades and exposed brick. Composed of naturally seasoned lime putty obtained by firing limestone with soft flame (wood), selected aggregates and mineral pigments, guaranteed free from cement and chemical additives.

The company takes on only the responsibility of the product until delivery, while the application, use and processing are the sole responsibility of the customer or the applicator. The company reserves the right to modify the composition over time while naturally keeping the characteristics unchanged.

The information on the technical data sheet refers to tests carried out with the material described and to our knowledge. Our materials are subject to continuous development; we, therefore, reserve the right to modify them at any time, without notice. We decline any responsibility for the incorrect use and application of materials other than those recommended.

